

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) Publication number:

**0 326 392 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**(45) Date of publication of patent specification: **09.03.94** (51) Int. Cl.<sup>5</sup> **C07D 301/10, C07D 303/04**(21) Application number: **89300776.5**(22) Date of filing: **27.01.89**

Consolidated with 89902677.7/0397793  
(European application No./publication No.) by  
decision dated 19.04.91.

(54) **Selective epoxidation of olefins.**

(30) Priority: **28.01.88 US 149297**  
**30.12.88 US 292589**

(43) Date of publication of application:  
**02.08.89 Bulletin 89/31**

(45) Publication of the grant of the patent:  
**09.03.94 Bulletin 94/10**

(94) Designated Contracting States:  
**AT BE CH DE ES FR GB GR IT LI LU NL SE**

(69) References cited:  
**EP-A- 0 003 642**  
**EP-A- 0 026 827**  
**FR-A- 2 523 971**

**CHEMICAL ABSTRACTS, vol. 105, no. 24, De-  
cember 1986, Columbus, Ohio, USA**

**GARFUNKEL, E.; DING, X.; DONG, G.; YANG,  
S.; HOU, X.; WANG, X. "The effect of sodium  
edlayers on the adsorption of oxygen on  
silver (100), page 347, column 1, abstract no.  
214 368m & Chin. Phys. Lett. 1985, 2(9),  
397-400**

(73) Proprietor: **EASTMAN KODAK COMPANY (a  
New Jersey corporation)**  
**343 State Street**  
**Rochester New York 14650(US)**

(72) Inventor: **Monnier, John Robert c/o Eastman  
Kodak Company**  
**Patent Department**  
**343 State Street**  
**Rochester New York 14650(US)**  
Inventor: **Muehlbauer, Peter James c/o East-  
man Kodak Company**  
**Patent Department**  
**343 State Street**  
**Rochester New York 14650(US)**

(74) Representative: **Baron, Paul Alexander Cliff-  
ford et al**  
**Kodak Limited**  
**Patent Department**  
**Headstone Drive**  
**Harrow Middlesex HA1 4TY (GB)**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

## Description

This invention relates to oxidation reactions. In one aspect, this invention relates to selective oxidation reactions for the production of epoxides from olefins.

### Background of the Invention

Epoxides are highly reactive chemical compounds which, as a result of their reactivity, can be used in a wide variety of applications. Unfortunately, due to the reactivity of epoxides, they are often difficult to prepare with high selectivity and in high yields. Ethylene is the only olefin which has been successfully oxidized employing molecular oxygen on a commercial scale to produce an epoxide.

Preferred catalysts employed for the oxidation of ethylene to produce ethylene oxide comprise silver on solid supports. When such catalysts are employed for the oxidation of olefins having no longer chain lengths than ethylene, no epoxides are obtained, but instead various higher oxidation products (up to and including carbon dioxide and water) are obtained.

Alternate routes to epoxides other than ethylene oxide include the non-catalytic oxidation of olefins with peroxides. Such processes are not only uneconomical, but are also hazardous due to the large quantities of peroxide required for the desired conversion.

It would, therefore, be desirable to be able to catalytically oxidize olefins having longer chain lengths than ethylene to produce epoxides directly. Such processes would provide large quantities of highly reactive olefin derivatives which would find a wide range of uses, such as for example, as polymer cross-linking agents, as reactive chemical intermediates, as precursors for the production of organic solvents, and the like.

### Objects of the Invention

An object of the present invention, therefore, is to provide a catalytic process for the selective oxidation of olefins having a longer chain length than ethylene to selectively produce epoxides in high yield.

This and other objects of the present invention will become apparent from inspection of the detailed description and appended claims which follow.

### Statement of the Invention

In accordance with the present invention, we have discovered that olefins having no allylic hydrogens can be catalytically oxidized to produce a high selectivity of epoxide derivatives thereof by contacting the olefin feed with an oxygen-containing gas in the presence of a silver catalyst and, optionally, an organic halide, under defined oxidation conditions. The practice of the present invention makes possible the selective, large scale production of such highly functionalized compounds as butadiene oxide, t-butyl ethylene oxide, vinyl furan oxide, and methyl epoxy vinyl ketone, employing readily available feedstocks (e.g., butadiene, t-butylethylene, vinyl furan, and methyl vinyl ketone, respectively). The only other materials consumed during the invention reaction, besides the olefin feedstock, are molecular oxygen (and organic halide, when employed). Thus, the invention process is not only economical, but, since the reaction can be run in the continuous mode, it also makes possible the ready preparation of large quantities of these useful chemical compounds. In addition, carrying out the oxidation reaction in the presence of organic halide gives improved product yield, increased catalyst lifetime, and improved catalyst thermal stability.

### Detailed Description of the Invention


In accordance with the present invention, we have developed a process for the selective epoxidation of olefins having defined structure which comprises contacting the feed olefin with a sufficient quantity of an oxygen-containing gas so as to maintain the molar ratio of olefin to oxygen in the range of 0.01 up to 20, in the presence of a silver catalyst and, optionally, an organic halide, at a reaction pressure in the range of 0.1 up to 100 atmospheres and a temperature in the range of about 75 up to 325°C for a reaction time sufficient to obtain olefin conversions per pass in the range of about 0.1 up to 75 mole percent.

Olefins contemplated for use in the practice of the present invention are N-vinylpyrrolidone or those which satisfy the following structural formula:




wherein each R is independently selected from:


- a) hydrogen,  
b) aryl and substituted aryl groups having in the range of 7 up to 20 carbon atoms,  
c) tertiary alkyl groups of the formula:



where each  $R'$  is independently:  
 $R''$ .



or



where R'' is H, C<sub>1</sub>-C<sub>10</sub> alkyl or substituted alkyl, an aryl or substituted aryl group having 6 up to 20 carbon atoms, and n is a whole number from 0-12;

- d)  $\text{CR}_3'-(\text{CR}_2')_x\text{-O-}$ , where  $x$  is a whole number from 1-12;



- f) R
- <sub>2</sub>
- ' N- :

- g)  $R''S-$  ;

- h)  $CR_2'' = CR'' \{CR'' = CR''\}_y$ , where  $y$  is an integer from 0-20; or

- ii




where X is 0, S or NR<sup>+</sup>; and m is an integer from 0 - 3.

with the proviso that said olefin have no allylic hydrogens and that at least one R-group not be hydrogen.

Exemplary olefins which satisfy the above structural formula include butadiene, tertiary butylethylene, vinyl furan, methyl vinyl ketone, N-vinyl pyrrolidone, and the like. A presently preferred olefin for the use in the practice of the present invention is butadiene because of its ready availability, relatively low cost, and

the wide range of possible uses for the epoxide reaction products.

The epoxides produced by the invention process have the structural formula:



wherein each R is independently defined as set forth above. Where one or more of the R-groups contain carbon-carbon bond unsaturation, further oxidation can be carried out in accordance with the present invention, thereby producing polyepoxide products.

The silver catalyst required for the practice of the present invention can be employed in either supported or unsupported forms.

When a support is employed, the loading level of silver on support typically falls within the range of about 0.1 up to 50 weight percent, calculated as elemental silver and based on the total weight of finished catalyst. Preferably, the loading level of silver on support falls within the range of about 1 up to 30 weight percent elemental silver; with loading levels in the range of about 2 up to 20 weight percent being most preferred.

It is presently preferred to apply the silver to a solid support for efficient use of the expensive silver component. Typical catalyst supports include

silica,  
alumina,  
silica-alumina,  
titanium oxide,  
lanthanum oxide,  
magnesium oxide,  
boron nitride,  
boron carbide,  
silicon nitride,  
silicon carbide,  
zinc oxide,  
tin oxide,

iron oxide,  
calcium oxide,  
barium oxide,  
strontium oxide,  
zirconium oxide,  
carbon,  
boron phosphate,  
zirconium phosphate,

and the like, as well as mixtures of any two or more thereof.

Typically, these solid supports will have a surface area of less than about 50 m<sup>2</sup>/g. Preferred supports will have a surface area of less than about 10 m<sup>2</sup>/g and will be neutral or moderately basic in character. The presently most preferred supports have surface areas of less than about 1 m<sup>2</sup>/g, and include alumina, silica, and silicon carbide.

The actual physical form of the catalyst support is not particularly important. While the form of the catalyst support has little effect on catalyst activity, practical considerations such as ease of heat transfer, mass transfer, pressure drop due to fluid flow restriction, efficiency of gas-liquid-solid contacting, catalyst durability, and the like make the use of defined shapes such as spheres, pellets, extrudates, rings, saddles, and the like preferred.

Especially preferred supports are those which have been treated with in the range of 0.001 up to 10 weight %, based on the total weight of catalyst, including support, of at least one promoter selected from:

the salts of alkali metal,  
the oxides of alkali metals,  
the salts of alkaline earth metals,  
the oxides of alkaline earth metal,  
organic halides,  
inorganic halides,

acid halides, or  
elemental halogens.

Exemplary salts of alkali metals include sodium nitrate, sodium sulfate, sodium chloride, sodium bromide, rubidium nitrate, rubidium acetate, lithium sulfate, lithium chloride, cesium nitrate, cesium chloride, cesium bromide, and the like; exemplary oxides of alkali metals include sodium oxide, sodium hydroxide, cesium oxide, cesium hydroxide, lithium oxide, lithium hydroxide, and the like; exemplary salts of alkaline earth metals include barium nitrate, barium acetate, calcium nitrate, calcium acetate, calcium chloride, and the like; exemplary oxides of alkaline earth metals including barium oxide, barium hydroxide, calcium oxide, calcium hydroxide, and the like; exemplary organic halides employed as catalyst promoter include carbon tetrachloride, carbon tetrabromide, chloroform, bromoform, methylene chloride, methylene bromide, ethylene dibromide, ethylene dichloride, methyl chloride, methyl bromide, ethyl chloride, ethyl bromide, dichloropropane, dichloroethylene, trichloroethylene, vinyl chloride, chlorobenzene, bromobenzene,  $\alpha$ -chlorotoluene, 2-chlorotoluene, and the like; exemplary inorganic halides include HCl, HBr, and the like; exemplary acid halides include HOCl, HOBr and the like; and the elemental halogens include chlorine, bromine and iodine. Those of skill in the art recognize that the above-recited compounds are merely illustrative of the compounds which are useful as promoters in the practice of the present invention, and that many other compounds which fall within the generic categories set forth above can also be identified and would be expected to also impart enhanced activity and/or selectivity to the catalyst employed in the practice of the present invention.

Of the above compounds, the alkali metal halides are the most preferred as catalyst promoters, i.e., for treatment of catalyst prior to contacting with molecular oxygen and the olefin to be oxidized. Exemplary preferred alkali metal halides include cesium chloride, rubidium chloride, potassium chloride, sodium chloride, sodium bromide, potassium bromide, rubidium bromide, cesium bromide, and the like.

Those of skill in the art recognize that catalysts employed in the practice of the present invention can include additional components which may modify catalyst activity and/or selectivity. Such additives may be incorporated into the finished catalyst because their presence aids catalyst preparation, e.g., binders, die lubricants, and the like; or additives may be incorporated as extenders to reduce the cost of catalyst preparation; or additives may be incorporated to extend the operating ranges for reaction temperature and/or pressure; or additives may be incorporated to increase catalyst lifetime under reaction conditions and/or to modify the amounts of catalyst promoters employed to produce enhanced catalyst activity. It is recognized, of course, that some additives (e.g., cesium) are suitably employed in very low levels (i.e., milligrams of additive per gram of catalyst); while other additives (i.e., binders, diluents, and the like) are suitably employed at significantly higher levels (i.e., as a significant percentage of the total catalyst weight).

Supported catalysts can be prepared employing techniques well known to those of skill in the art, such as, for example, by precipitation of the active metals on the support, by impregnation, by coprecipitation of support and active metals, by grinding together solid support and active metal(s) in particulate form; and the like. When a promoter is also present in the catalyst, the order in which it is incorporated into the catalyst is not critical, i.e., support can be contacted with a silver source, then promoter; or support can be contacted with promoter, then a silver source; or support can be contacted simultaneously with both promoter and a silver source; and other such variations.

Most any source of silver is suitable for use in preparing the catalyst employed in the practice of the present invention. Since a preferred method for preparation of supported catalyst involves impregnation of support with a solution of a silver compound, soluble silver compounds are a presently preferred source of silver. Exemplary compounds are silver nitrate, silver oxalate, silver acetate, and the like. Those of skill in the art recognize that certain organic silver compounds require the addition of ammonia or an amine in order to solubilize the organic silver compound in aqueous medium; thus, the use of such solvation-promoting additives is contemplated in the practice of the present invention.

The process of the present invention is carried out by contacting the olefin to be oxidized with molecular oxygen and, optionally, an organic halide under oxidation conditions, i.e., in the presence of sufficient quantities of an oxygen-containing gas to provide a molar ratio of olefin to oxygen in the range of about 0.01 up to 20, and in the presence of 0 up to about 1000 parts per million (by volume of total feed) of organic halide. When employed, preferred quantities of organic halide for use in the practice of this optional embodiment of the present invention fall within the range of about 1 up to 100 parts per million, by volume of total feed.

While greater or lesser quantities of molecular oxygen can be employed, sufficient quantities of oxygen should be provided to insure that undesirably low levels of olefin conversion do not occur, while excessively high oxygen concentrations should be avoided to prevent the formation of explosive mixtures. Similarly, lower levels of organic halide will provide negligible effect on catalyst performance, while higher levels of

organic halide would not be expected to provide any significant improvement in catalyst performance.

Suitable oxygen-containing gases include air, oxygen-enriched air, substantially purified oxygen, oxygen diluted with inert gases such as  $N_2$ , Ar,  $CO_2$ , or  $CH_4$ , and the like.

Organic halides contemplated by the optional co-feed embodiment of the present invention include  
 5 compounds of the structure  $R^*X$ , wherein  $R^*$  is a hydrocarbyl radical or halogenated hydrocarbyl radical having in the range of 1 up to 8 carbon atoms, and X is any one of the halogens, preferably chlorine or bromine, and wherein  $R^*$  contains at least one hydrogen atom which is sufficiently acidic so as to render  $R^*X$  capable of undergoing dehydrohalogenation under the reaction conditions. Exemplary organic halides include  $C_1$  compounds such as methyl chloride, methyl bromide, methylene chloride, methylene bromide,  
 10 chloroform and bromoform, and the like;  $C_2$  compounds such as ethyl chloride, ethyl bromide, dichloroethane, dibromoethane, vinyl chloride, dichloroethylene, trichloroethylene, and the like;  $C_3$  compounds such as dichloropropane, dibromopropane, dichloropropene, dibromopropene, and the like;  $C_4$  compounds such as chlorobutane, bromobutane, dichlorobutane, dibromobutane, chlorobutene, bromobutene, dichlorobutene, dibromobutene, and the like;  $C_5$  compounds such as mono-, di-, tri-, tetra- and pentachloropentanes or pentenes, mono-, di-, tri-, tetra-, and pentabromopentanes or pentenes, cyclopentylchloride,  
 15 cyclopentylbromide, and the like;  $C_6$  compounds such as mono-, di-, tri-, tetra-, penta- and hexachlorohexanes or hexenes, mono-, di-, tri-, tetra-, penta- and hexabromohexanes or hexenes, cyclohexylchloride, cyclohexylbromide, chlorobenzene, bromobenzene, and the like;  $C_7$  compounds such as chlorotoluene, bromotoluene, benzyl chloride, benzyl bromide, mono-, di-, tri-, tetra-, penta-, hexa- and heptachloroheptanes or heptenes, mono-, di-, tri-, tetra-, penta-, hexa-, and heptabromoheptanes or heptenes,  
 20 chlorocycloheptane, bromocycloheptane, and the like;  $C_8$  compounds such as mono-, di-, tri-, tetra-, penta-, hexa-, hepta- and octachlorooctanes or octenes, mono-, di-, tri-, tetra-, penta-, hexa-, hepta-, and octabromooctanes or octenes, and the like; as well as mixtures of any two or more thereof.

When employed, the organic halide can be added to the oxidation reaction zone in a variety of ways.  
 25 For example, it can be mixed with the olefin to be oxidized and/or the oxygen-containing gas prior to contacting with the catalyst, or the organic halide can be introduced to the reaction zone separately from the feed olefin and/or the oxygen-containing gas.

Suitable reaction temperatures fall within the range of about 75 up to 325 °C. At lower temperatures, the reaction proceeds so slowly as to be impractical, while at higher temperatures undesirable levels of by-products, e.g., carbon dioxide, are obtained. Preferred reaction temperatures fall within the range of about  
 30 125 up to 275 °C; with temperatures in the range of about 175 up to 250 °C being most preferred because selectivity to the desired epoxide falls off at temperatures significantly above 250 °C and space-time yields are undesirably low at temperatures below about 175 °C.

The reaction pressure can vary within wide ranges, with typical limits of about 0.1 up to 100 atmospheres being chosen primarily as a function of safety, handling, equipment and other practical considerations. Preferably, reaction pressure is maintained in the range of about 1 up to 30 atmospheres.

Reaction times suitable for the practice of the present invention can vary within wide ranges. Generally, olefin, oxygen, organic halide and catalyst are maintained in contact for a time sufficient to obtain olefin conversions per pass in the range of about 0.1 up to 75 mole percent. Preferred target olefin conversion  
 40 levels per pass fall within the range of about 1 up to 50 mole percent, while reaction times sufficient to obtain olefin conversion per pass in the range of about 5 up to 30 mole percent are presently most preferred for efficient utilization of the reactor capacity.

Those of skill in the art recognize that the actual contact times required to accomplish the desired conversion levels can vary within wide ranges, depending on such factors as vessel size, olefin to oxygen ratios, the silver loading level on the catalyst, the presence or absence of any catalyst modifiers (and their loading levels), the amount of organic halide present in the reaction zone, the reaction temperature and pressure, and the like.

The invention process can be carried out in either batch or continuous mode. Continuous reaction is presently preferred since high reactor throughput and high purity product is obtained in this manner. The  
 50 batch mode is satisfactorily employed when high volume of reactant throughput is not required, for example, for liquid phase reactions.

For continuous mode of reaction carried out in the gas phase, typical gas hourly space velocities (GHSV) fall within the range of about 100 up to 30,000  $hr^{-1}$ . GHSV in the range of about 200 up to 20,000  $hr^{-1}$  are preferred, with GHSV in the range of about 300 up to 10,000  $hr^{-1}$  being most preferred because  
 55 under such conditions the most desirable combination of feed olefin conversion and product selectivities are obtained.

When continuous mode of reaction is carried out in the liquid phase, typical liquid hourly space velocities (LHSV) employed will give contact times analogous to that obtained at the GHSV values given

above. Most preferably, LHSV employed will fall in a range so as to produce the most desirable combination of feed olefin conversion levels and high product selectivity.

Recovery of product produced in the practice of the present invention can readily be carried out employing techniques well known by those of skill in the art. For example, where reaction is carried out in the continuous mode, unreacted starting material is initially separated from reaction products; and the desired product then isolated from the resulting product mixture by distillation, crystallization, extraction, or the like. Since the selectivity to the desired epoxide product is generally quite high, there are only small amounts of undesired reaction products from which to isolate the desired product.

The invention will now be described in greater detail by reference to the following non-limiting examples.

#### EXAMPLE 1 - Catalyst Preparation

Catalysts were typically prepared by impregnation of support with a solution of a silver compound (and optionally a promoter) in 0.5-2 volumes of solvent relative to the volume of support being treated.

Thus, for example, a 14.2% Ag (as determined by neutron activation analysis) on  $\text{Al}_2\text{O}_3$  support was prepared by dissolving 202.3 grams of Kodak silver nitrate in 500 mL of distilled water. Five hundred grams of calcined  $\text{Al}_2\text{O}_3$  3/16" spheres (surface area 0.39  $\text{m}^2/\text{g}$ , total pore volume 0.36 cc(Hg)/gm, median pore diameter 5.4 $\mu$ , packing density 0.94  $\text{g}/\text{cm}^3$ , crush strength 65.2 pounds, chemical composition (wt %):  $\text{Al}_2\text{O}_3$  - 86.1,  $\text{SiO}_2$  - 11.8,  $\text{Fe}_2\text{O}_3$  - 0.2,  $\text{TiO}_2$  - 0.1,  $\text{CaO}$  - 0.4,  $\text{MgO}$  - 0.4,  $\text{Na}_2\text{O}$  - 0.4,  $\text{K}_2\text{O}$  - 0.6) were added to the silver-containing solution, the mixture tumbled for 30 minutes at 50°C, then water removed under vacuum at 60°C. The resulting pellets were then dried for 30 minutes at 120°C in a forced air oven. This material could be calcined and used directly for oxidation of olefin feed or treated with a promoter and then calcined.

Prior to catalyst evaluation (and either before or after further treatment with promoter), all catalysts were optionally calcined in an oxygen-containing atmosphere (air or oxygen-supplemented helium) at about 350°C for about 4 hours. Following calcination, all catalysts employed in the following examples were subjected to an activation treatment at a temperature in the range of about 300-350°C in an atmosphere initially containing about 2-5% hydrogen in an inert carrier such as helium or nitrogen. The hydrogen content of the activating atmosphere was gradually increased up to a final hydrogen concentration of about 20-25% at a controlled rate so that the activation temperature did not exceed 350°C. After the temperature was maintained for about 1 hour at a hydrogen concentration in the range of about 20-25%, catalyst was ready for use.

When a Ag/ $\text{Al}_2\text{O}_3$  catalyst was treated with promoter, a quantity of catalyst was contacted with 0.5-2 volumes of aqueous promoter, then dried as previously described. In this way, the catalysts summarized in Table I were prepared. Unless otherwise noted in the Table, catalyst support employed was a fluidizable powder having a surface area of 0.26  $\text{m}^2/\text{g}$ , a total pore volume of 0.675 cc (Hg)/gm, median pore diameter 19 $\mu$ , a packing density of 0.98  $\text{g}/\text{cm}^3$ , and a chemical composition (wt %) as follows:  $\text{Al}_2\text{O}_3$  - 84.7,  $\text{SiO}_2$  - 13.4,  $\text{Fe}_2\text{O}_3$  - 0.21,  $\text{TiO}_2$  - 0.47,  $\text{CaO}$  - 0.21,  $\text{MgO}$  - 0.12,  $\text{Na}_2\text{O}$  - 0.15,  $\text{K}_2\text{O}$  - 0.26:

Table I  
Alumina-Supported Catalysts

| Catalyst | Silver loading,<br>(silver source) | Support   | Promoter loading,<br>mg/g*<br>(Promoter Source) |
|----------|------------------------------------|---|---|
| A        | 1.1 (AgNO <sub>3</sub> )           | Al <sub>2</sub> O <sub>3</sub>                        | 0   |
| A'       | 5.3 (AgNO <sub>3</sub> )           | Al <sub>2</sub> O <sub>3</sub>                        | 0   |
| B        | 15.2 (AgNO <sub>3</sub> )          | Al <sub>2</sub> O <sub>3</sub> (pellets) <sup>1</sup> | 0   |
| B'       | 15 (AgNO <sub>3</sub> )            | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 0   |
| B''      | 15 (AgNO <sub>3</sub> )            | Al <sub>2</sub> O <sub>3</sub> (rings) <sup>3</sup>   | 0   |
| C        | 17 (AgNO <sub>3</sub> )            | Al <sub>2</sub> O <sub>3</sub>                        | 0   |
| D        | 19 (AgNO <sub>3</sub> )            | Al <sub>2</sub> O <sub>3</sub>                        | 0   |
| E        | 38 (AgNO <sub>3</sub> )            | Al <sub>2</sub> O <sub>3</sub>                        | 0   |
| F        | 5 (AgNO <sub>3</sub> )             | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 1.0 (CsCl)                                      |
| G        | 15 (AgNO <sub>3</sub> )            | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>4</sup> | 1.0 (CsCl)                                      |
| H        | 15 (AgNO <sub>3</sub> )            | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 1.0 (CsCl)                                      |



Table I (Cont'd.)  
Alumina-Supported Catalysts

| <u>Catalyst</u> | <u>Silver loading,<br/>wt %<br/>(silver source)</u> | <u>Support</u>  | <u>Promoter loading,<br/>mg/g**<br/>(Promoter Source)</u> |
|-----------------|---|---|---|
| I               | 15 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 1.25 (CsCl)   |
| J               | 15 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 1.50 (CsCl)   |
| K               | 15 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 1.0/0.024 (CsCl/Br <sub>2</sub> )**                       |
| L               | 15 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 1.0/0.056 (CsCl/Br <sub>2</sub> )**                       |
| M               | 15 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 1.0/0.12 (CsCl/Br <sub>2</sub> )**                        |
| N               | 15 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 1.0/0.24 (CsCl/Br <sub>2</sub> )**                        |
| O               | 15 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> (spheres) <sup>2</sup> | 1.0/0.24 (CsCl/Br <sub>2</sub><br>+ H <sub>2</sub> O)***  |
| P               | 17 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub>                        | 1.0 (CsCl)  |
| Q               | 17 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub>                        | 0.44 (KCl)  |
| R               | 17 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub>                        | 1.33 (KCl)  |
| S               | 17 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub>                        | 1.42 (RbCl)   |

Table I (Cont'd.)  
Alumina-Supported Catalysts

| Catalyst | Silver loading,<br>wt %<br>(silver source)          | Support                        | Promoter loading,<br>mg/g*<br>(Promoter Source) |
|----------|---|--------------------------------|---|
| T        | 17 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> | 0.36 (RbCl)                                     |
| U        | 17 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> | 3.1 (Ba(NO <sub>3</sub> ) <sub>2</sub> )        |
| V        | 17 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> | 1.45 (BaCl <sub>2</sub> )                       |
| W        | 17 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> | 0.24 (Br <sub>2</sub> )**                       |
| X        | 17 (AgNO <sub>3</sub> )                             | Al <sub>2</sub> O <sub>3</sub> | 1.76 (RbNO <sub>3</sub> )                       |
| Y        | 18.9 (AgNO <sub>3</sub> )                           | Al <sub>2</sub> O <sub>3</sub> | 1.0 (CsCl)                                      |
| Z        | 18.9 (AgNO <sub>3</sub> )                           | Al <sub>2</sub> O <sub>3</sub> | 1.26 (CsBr)                                     |
| AA       | 18.9 (AgNO <sub>3</sub> )                           | Al <sub>2</sub> O <sub>3</sub> | 1.16 (CsNO <sub>3</sub> )                       |
| BB       | 19 (Ag <sub>2</sub> C <sub>2</sub> O <sub>4</sub> ) | Al <sub>2</sub> O <sub>3</sub> | 0   |

Table I (Cont'd.)

## Alumina-Supported Catalysts

- \*milligram of promoter (based on weight of promoter compound) per gram of silver-treated support.
- \*\*prepared by dissolving elemental Br<sub>2</sub> in carbon tetrachloride (CCl<sub>4</sub>), then the Br<sub>2</sub>-CCl<sub>4</sub> solution was added to support which had previously been treated with silver and promoter (if employed); after mixing, then soaking for about 30 minutes, the CCl<sub>4</sub> was removed by evaporation on a rotary evaporator, and finally catalyst was calcined and reduced as described above.
- \*\*\*As in \*\* above, Br<sub>2</sub> was dissolved in CCl<sub>4</sub>, then enough water added to produce a two-phase system, which was then added to the previously Ag- and Cs-treated support; after soaking for about 30 minutes, catalyst was dried, calcined and reduced as described above.
- 1<sub>3</sub>/16" pellets with a surface area of 0.26 m<sup>2</sup>/g, a total pore volume of 0.23 cc(Hg)/gm, median pore diameter of 19μ, a packing density of 0.90 g/cm<sup>3</sup>, and a chemical composition (wt %) as follows: alumina - 84.7, SiO<sub>2</sub> - 13.4, Fe<sub>2</sub>O<sub>3</sub> - 0.21, TiO<sub>2</sub> - 0.47, CaO - 0.21, MgO - 0.12, Na<sub>2</sub>O - 0.15, K<sub>2</sub>O - 0.26.
- 2<sub>3</sub>/16" spheres with a surface area of 0.39 m<sup>2</sup>/g, a total pore volume of 0.36 cc(Hg)/gm, median pore diameter of 5.4μ, a packing density of 0.94 g/cm<sup>3</sup> and a chemical composition (wt %) as follows: Al<sub>2</sub>O<sub>3</sub> - 86.1, SiO<sub>2</sub> - 11.8, Fe<sub>2</sub>O<sub>3</sub> - 0.2, TiO<sub>2</sub> - 0.1, CaO - 0.4, MgO - 0.4, Na<sub>2</sub>O - 0.4, K<sub>2</sub>O - 0.6.

Table I (Cont'd.)  
Alumina-Supported Catalysts

|   |
|---|
| 3 1/4" rings having a surface area of 0.43 m <sup>2</sup> /g, a total pore volume of 0.37 cc (Hg)/gm, a median pore diameter of 7μ, a packing density of 0.80 g/cm <sup>3</sup> , and a chemical composition (wt %) as follows: Al <sub>2</sub> O <sub>3</sub> - 93.1, SiO <sub>2</sub> - 5.6, Fe <sub>2</sub> O <sub>3</sub> - 0.3, TiO <sub>2</sub> - 0.1, CaO - 0.1, MgO - 0.3, Na <sub>2</sub> O - 0.1, K <sub>2</sub> O - 0.1. |
| 4 1/16" spheres having a surface area of 0.13 m <sup>2</sup> /g, a total pore volume of 0.37 cc (Hg)/gm, a median pore diameter of 32.5μ, a packing density of 0.88 g/cm <sup>3</sup> , and a chemical composition (wt %) as follows: Al <sub>2</sub> O <sub>3</sub> - 85.0, SiO <sub>2</sub> - 12.0, and the remaining 3% as Fe <sub>2</sub> O <sub>3</sub> , TiO <sub>2</sub> , CaO, MgO, Na <sub>2</sub> O and K <sub>2</sub> O. |

Silver was deposited on other supports as well, following the same general procedure as above. Thus, 8.0% Ag on ZnO was prepared by dissolving 0.26 g of AgNO<sub>3</sub> in 10 mL of distilled water, then adding to the solution 2 g of uncalcined ZnO (having a surface area of 3.9 m<sup>2</sup>/g, and a particle diameter in the range of about 75-150μ). This material was then dried as described above and is designated as Catalyst CC.

Titania supported catalyst was prepared by calcining TiO<sub>2</sub> (having a surface area of about 0.5 m<sup>2</sup>/g, a particle diameter in the range of about 40-75μ) in oxygen at 450° for about 4 hours. Three grams of this treated TiO<sub>2</sub> was then slurried in about 10 mL of distilled water, to which was added a solution of about 10 mL of distilled water containing 73 mg of AgNO<sub>3</sub>. The combination was thoroughly mixed, then dried as described above. The resulting catalyst, containing about 1.9% Ag, is designated as Catalyst DD.

A higher silver loading-titania supporting catalyst was prepared by slurrying 3 g of TiO<sub>2</sub> calcined as described above in 15 mL of distilled water, then slowly adding to the slurry a solution of 0.26 g of AgNO<sub>3</sub>.

in about 10 mL of distilled water. The mixture was heated for about 1 hour to 80-90 °C, then enough formaldehyde was added dropwise until no further silver was precipitated upon addition of HCl to an aliquot of the supernatant liquid. The resulting catalyst had a silver loading of 5.2% and is designated Catalyst EE.

A calcium oxide supporting catalyst was prepared by adding 2.0 g of calcined CaO to 10 mL of distilled water in which was dissolved 0.26 g of silver nitrate. The mixture was warmed to -50 °C for -1 hour, then water was removed under reduced pressure on a rotary evaporator at a temperature of about 60-70 °C, and the sample then dried by placing in a forced air oven at 120 °C for 1 hour. The resulting catalyst is referred to as Catalyst FF.

A silica-supported catalyst was prepared as per the general procedure set forth above using a silica support having a surface area of 0.18 m<sup>2</sup>/g, and a particle diameter in the range of 75-250 μ. The resulting catalyst had a silver loading of 5 wt % and is designated as Catalyst GG.

A barium oxide supported catalyst was prepared as per the general procedure set forth above using a barium oxide support having a surface area of about 1 m<sup>2</sup>/g, and a particle diameter in the range of about 40-75 μ. The resulting catalyst had a silver loading of 6.3 wt % and is designated as Catalyst HH.

Boron nitride (BN; Catalyst II), silicon nitride (Si<sub>3</sub>N<sub>4</sub>; Catalyst JJ) and silicon carbide (SiC; Catalyst KK) supported catalysts were prepared in accordance with the standard procedure set forth above. In each case, support was contacted with the necessary amount of aqueous silver nitrate to achieve a 5 wt % Ag on support catalyst. After soaking for about 30 minutes, water was removed on a rotary evaporator, catalyst dried in a forced air oven at 120 °C, then catalyst loaded into a reactor for in situ activation, which consisted of calcination for 4 hrs. at 350 °C in a stream of 20% O<sub>2</sub>/80% He, followed by reduction for 1 hr. at 350 °C in a stream of 20% H<sub>2</sub>/80% He. The catalyst designations, supports used and support properties are summarized below.

| Support (surface area)                | Resulting 5 wt %<br>Ag catalyst |
|---------------------------------------|---------------------------------|
| BN (2.9)                              | II                              |
| Si <sub>3</sub> N <sub>4</sub> (11.9) | JJ                              |
| SiC (0.12)                            | KK                              |

#### EXAMPLE 2 - Effect of Silver Loading Level

In all of the following catalyst evaluation runs, catalysts were evaluated under steady state conditions in a 1 atmosphere, single-pass flow reactor system. The reactor tube was constructed of pyrex and the catalyst charge (between 0.1 and 20.0 g) was held in place by means of a pyrex frit. The geometries of the reactor and catalyst particles as well as bed depth were chosen to maintain and measure the true kinetic and catalytic aspects of the reaction. Gas hourly space velocities for all experiments fell within the range of about 200 up to 3000 hr<sup>-1</sup>. A chromel/alumel thermocouple sheathed in stainless steel was embedded within the catalyst bed to measure the true reaction temperature.

The feed gases C<sub>4</sub>H<sub>6</sub> and O<sub>2</sub>, as well as the diluent He, were added using mass flow controllers, which permitted highly accurate and reproducible flow rates of C<sub>4</sub>H<sub>6</sub>, O<sub>2</sub>, and He regardless of pressure changes from the supply cylinders or the reactor system downstream from the controllers.

Reaction product analyses (as well as feed composition analyses) were made using an in-line gas sampling loop connected directly to the inlet of a Varian 3760 gas chromatograph. Both thermal conductivity (TC) and flame ionization (FI) detectors [(connected in series below the packed Chromosorb 101 column (8 ft. by 2mm id pyrex capillary column))] were used to analyze all of the reaction products. The TC detector gave quantitative analyses for O<sub>2</sub>, CO<sub>2</sub>, H<sub>2</sub>O and HCHO (if present), while the FI detector was used for organic molecules such as C<sub>4</sub>H<sub>6</sub>, butadiene monoxide, crotonaldehyde, 2,5-dihydrofuran, furan and acrolein. In practice, however, usually only the selective epoxidation product and olefin feedstock were present as organic molecules. Further, by means of a switching valve, it was possible to divert the feed stream through the in-line sample loop prior to passage over the catalyst. In this way, quantitative analysis of the feed stream and comparison to the corresponding data from the reactor effluent were possible, thereby providing very accurate measurements of both conversion levels and product selectivities. Output from both the TC and FI detectors were integrated using computing integrators which were programmed to give both absolute quantities and rates of formation. All reactor exit lines were heated and maintained at 125-140 °C to prevent product condensation.

The GC analysis was performed using the following temperature programming schedule: an initial temperature of 100 °C was held for 5 minutes, followed by a temperature program rate of + 10 °C/min up to a final temperature of 200 °C which was then held for 7 minutes. The helium GC carrier rate was 20 mL/min.

- 5 In this example, the effect of silver loading level on feed olefin conversion and product selectivity (based on the moles of olefin converted) was investigated. Reaction parameters and results are presented in Table 2.

10

15

20

25

30

35

40

45

50

55

Table 2

| Catalyst  | Reaction Parameters |   | C <sub>4</sub> H <sub>6</sub><br>Conversion,<br>% | Product<br>Selectivity<br>%*** |
|---|---------------------|---|---|--------------------------------|
|   | Temp,<br>°C         | Gas Feed**<br>(He/O <sub>2</sub> /C <sub>4</sub> H <sub>6</sub> ) | Total Gas<br>Flow (in mL<br>(STP)/min)            |                                |
| Ag powder                                       | 225                 | 0:1:1   | 17.6  | 70                             |
| Ag <sub>2</sub> O*                              | 225                 | 0:1:1   | 17.6  | 60                             |
| A (1.1% Ag on Al <sub>2</sub> O <sub>3</sub> )  | 250                 | 0:1:1   | 20  | 68                             |
| A' (5% Ag on Al <sub>2</sub> O <sub>3</sub> )   | 250                 | 0:1:1   | 20  | 74                             |
| B (15% Ag on Al <sub>2</sub> O <sub>3</sub> )   | 250                 | 0:1:1   | 18  | 67                             |
| B' (15% Ag on Al <sub>2</sub> O <sub>3</sub> )  | 250                 | 0:1:1   | 18.6  | 68                             |
| B'' (15% Ag on Al <sub>2</sub> O <sub>3</sub> ) | 250                 | 0:1:1   | 16.6  | 71                             |
| C (17% Ag on Al <sub>2</sub> O <sub>3</sub> )   | 250                 | 0:1:1   | 18.5  | 75                             |
| C (17% Ag on Al <sub>2</sub> O <sub>3</sub> )   | 225                 | 0:1:1   | 18.5  | 88                             |
| D (19% Ag on Al <sub>2</sub> O <sub>3</sub> )   | 250                 | 0:1:1   | 17.4  | 81                             |

Table 2 (Cont'd)

| Catalyst                                      | Reaction Parameters |   |  | C <sub>4</sub> H <sub>6</sub><br>Conversion,<br>% | Product<br>Selectivity<br>%*** |
|---|---------------------|---|--|---|--------------------------------|
|   | Temp,<br>°C         | Gas Feed**<br>(He/O <sub>2</sub> /C <sub>4</sub> H <sub>6</sub> ) | Total Gas<br>Flow (in mL<br>(STP)/min) |   |                                |
| E (38% Ag on Al <sub>2</sub> O <sub>3</sub> ) | 250                 | 0:1:1   | 18.8                                   | 2.7   | 89                             |

\*Grade 1 Ag<sub>2</sub>O powder was used as obtained from the supplier, activated by heating at 350°C in flowing hydrogen. The temperature was maintained at about 350°C by initially introducing 5% H<sub>2</sub> in He, with the hydrogen content gradually increased to about 20% (remainder He), and conditions of 20% H<sub>2</sub>/80% He and 350°C maintained for one hour before reactant feed commenced.

\*\*Volumetric ratio

\*\*\*Product selectivity is reported as selectivity to epoxide based on the moles of olefin converted.

The above results demonstrate that high catalyst activity and selectivity are obtained with both unsupported silver, and supported silver catalysts over a wide range of loading levels. As one might expect, higher activities are obtained at higher silver loading levels. It is of note that selectivity is not adversely affected even at increasing butadiene conversion levels.



## EXAMPLE 3 - Effect of Adding Promoters

A series of catalyst evaluations were carried out employing the same experimental setup described in Example 2. A variety of promoted catalysts were tested, with reaction parameters and results set forth in Table 3.

Table 3

| Catalyst   | Reaction Parameters |  |                                | C <sub>4</sub> H <sub>6</sub> Conversion, % | Product Selectivity, %*** |
|--|---------------------|--|--------------------------------|---|---------------------------|
|  | Temp, °C            | Gas Feed (He/O <sub>2</sub> /C <sub>4</sub> H <sub>6</sub> ) | Total Gas Flow in mL (STP)/min |   |                           |
| A (1.1% Ag/Al <sub>2</sub> O <sub>3</sub> )        | 250                 | 0:1:1  | 20                             | 0.8   | 68                        |
| A + 1.0 mg (CsCl per g. catalyst                   | 250                 | 0:1:1  | 20                             | 10.0  | 96                        |
| F ((CsCl)-5% Ag/Al <sub>2</sub> O <sub>3</sub> )   | 225                 | 0:1:1  | 20                             | 4.5   | 94                        |
|  | 250                 | 0:1:1  | 20                             | 9.5   | 88                        |
| B' (15% Ag/Al <sub>2</sub> O <sub>3</sub> spheres) | 225                 | 0:1:1  | 21.0                           | 0.5   | 87                        |
|  | 250                 | 0:1:1  | 18.6                           | 1.4   | 68                        |
| H ((CsCl)-15% Ag/Al <sub>2</sub> O <sub>3</sub> )  | 225                 | 0:1:1  | 20                             | 15  | 93                        |
|  | 250                 | 0:1:1  | 20                             | 23  | 89                        |
| G ((CsCl)-15% Ag/Al <sub>2</sub> O <sub>3</sub> )  | 225                 | 0:1:1  | 20                             | 9.4   | 94                        |
| I ((CsCl)-15% Ag/Al <sub>2</sub> O <sub>3</sub> )  | 225                 | 0:1:1  | 18.2                           | 9.8   | 93                        |
|  | 225                 | 0:1:1  | 40.5                           | 9.5   | 95                        |
|  | 225                 | 0:1:1  | 82.2                           | 9.2   | 95                        |
|  | 250                 | 0:1:1  | 18.2                           | 16  | 95                        |

Table 3 (Cont'd)

| Catalyst   | Temp,<br>°C | Reaction Parameters   |                                |       | C <sub>4</sub> H <sub>6</sub><br>Conversion,<br>% | Product<br>Selectivity,<br>%*** |
|--|-------------|---|--------------------------------|-------|---|---------------------------------|
|  |             | Gas Feed<br>(He/O <sub>2</sub> /C <sub>4</sub> H <sub>6</sub> ) | Gas Flow<br>in mL<br>(STP)/min | Total |   |                                 |
| J ((CsCl)-15% Ag/Al <sub>2</sub> O <sub>3</sub> )                        | 225         | 0:1:1   | 16.1                           |       | 7.7   | 93                              |
|  | 225         | 0:1:1   | 35.5                           |       | 7.3   | 95                              |
|  | 240         | 0:1:1   | 35.5                           |       | 11.3  | 93                              |
|  | 250         | 0:1:1   | 16.1                           |       | 11.5  | 90                              |
| K ((CsCl & Br <sub>2</sub> )-<br>15% Ag/Al <sub>2</sub> O <sub>3</sub> ) | 225         | 0:1:1   | 17.4                           |       | 10  | 94                              |
|  | 225         | 0:1:1   | 38.0                           |       | 9.9   | 95                              |
|  | 240         | 0:1:1   | 38.0                           |       | 14  | 93                              |
| L ((CsCl & Br <sub>2</sub> )-<br>15% Ag/Al <sub>2</sub> O <sub>3</sub> ) | 250         | 0:1:1   | 17.4                           |       | 14  | 90                              |
|  | 225         | 0:1:1   | 17.1                           |       | 10.5  | 94                              |
|  | 225         | 0:1:1   | 38.0                           |       | 9.8   | 95                              |
|  | 250         | 0:1:1   | 17.1                           |       | 16  | 93                              |

Table 3 (Cont'd)

| Catalyst   | Reaction Parameters |   |   | C <sub>4</sub> H <sub>6</sub><br>Conversion,<br>% | Product<br>Selectivity,<br>%*** |
|--|---------------------|---|---|---|---------------------------------|
|  | Temp.,<br>°C        | Gas Feed<br>(He/O <sub>2</sub> /C <sub>4</sub> H <sub>6</sub> ) | Total<br>Gas Flow<br>in mL<br>(STP)/min |   |                                 |
| M ((CsCl & Br <sub>2</sub> )-<br>15% Ag/Al <sub>2</sub> O <sub>3</sub> ) | 225                 | 0:1:1   | 17.6                                    | 8   | 94                              |
|  | 225                 | 0:1:1   | 39.0                                    | 7.2   | 96                              |
|  | 240                 | 0:1:1   | 39.0                                    | 11.8  | 94                              |
|  | 240                 | 0:1:1   | 55.0                                    | 11.1  | 94                              |
|  | 250                 | 0:1:1   | 17.6                                    | 12  | 91                              |
| N ((CsCl & Br <sub>2</sub> )-<br>15% Ag/Al <sub>2</sub> O <sub>3</sub> ) | 225                 | 0:1:1   | 16.5                                    | 6.8   | 93                              |
|  | 225                 | 0:1:1   | 36.8                                    | 6.4   | 95                              |
|  | 240                 | 0:1:1   | 36.8                                    | 10.3  | 93                              |
|  | 250                 | 0:1:1   | 16.5                                    | 11.3  | 89                              |

Table 3 (Cont'd)

| Catalyst   | Reaction Parameters |   |   | C <sub>4</sub> H <sub>6</sub><br>Conversion,<br>% | Product<br>Selectivity,<br>%*** |
|--|---------------------|---|---|---|---------------------------------|
|  | Temp.,<br>°C        | Gas Feed<br>(He/O <sub>2</sub> /C <sub>4</sub> H <sub>6</sub> ) | Total<br>Gas Flow<br>in mL<br>(STP)/min |   |                                 |
| O ((CsCl & Br <sub>2</sub> )-<br>15% Ag/Al <sub>2</sub> O <sub>3</sub> ) | 225                 | 0:1:1   | 17.2                                    | 4.4   | 90                              |
|  | 225                 | 0:1:1   | 36.4                                    | 4.0   | 93                              |
|  | 240                 | 0:1:1   | 36.4                                    | 7.5   | 90                              |
|  | 240                 | 4:1:1   | 56.6                                    | 7.3   | 87                              |
|  | 240                 | 0:1:1   | 70.6                                    | 7.1   | 93                              |
|  | 240                 | 2:1:1   | 72.3                                    | 7.6   | 90                              |
|  | 240                 | 1:1:1   | 80.0                                    | 8.3   | 92                              |
|  | 250                 | 0:1:1   | 17.2                                    | 8   | 85                              |
| C (17% Ag/Al <sub>2</sub> O <sub>3</sub> )                               | 225                 | 0:1:1   | 18.5                                    | 1.1   | 88                              |
|  | 250                 | 0:1:1   | 18.5                                    | 2.6   | 75                              |
| P (CsCl-17% Ag/Al <sub>2</sub> O <sub>3</sub> )                          | 225                 | 0:1:1   | 18.0                                    | 5.5   | 97                              |
|  | 250                 | 0:1:1   | 18.0                                    | 11  | 96                              |

Table 3 (Cont'd)

|  | Reaction Parameters |   |     |       | Temp.,<br>°C | Catalyst | Gas Feed<br>(He/O <sub>2</sub> /C <sub>4</sub> H <sub>6</sub> ) | Total<br>Gas Flow<br>in mL<br>(STP)/min | C <sub>4</sub> H <sub>6</sub><br>Conversion,<br>% | Product<br>Selectivity,<br>%*** |
|--|---------------------|---|-----|-------|--------------|----------|---|---|---|---------------------------------|
|  |                     |   |     |       |              |          |   |   |   |                                 |
|  | Q                   | (KCl-17% Ag/Al <sub>2</sub> O <sub>3</sub> )                                    | 225 | 0:1:1 | 18.9         | 0.2      | 96  |   |   |                                 |
|  |                     |   | 250 | 0:1:1 | 18.9         | 0.5      | 74  |   |   |                                 |
|  | R                   | (KCl-17% Ag/Al <sub>2</sub> O <sub>3</sub> )                                    | 225 | 0:1:1 | 18.6         | 0.1      | 98  |   |   |                                 |
|  |                     |   | 250 | 0:1:1 | 18.6         | 0.4      | 75  |   |   |                                 |
|  | S                   | (RbCl-17% Ag/Al <sub>2</sub> O <sub>3</sub> )                                   | 225 | 0:1:1 | 18.4         | 2.4      | 95  |   |   |                                 |
|  |                     |   | 250 | 0:1:1 | 18.4         | 5.5      | 89  |   |   |                                 |
|  | T                   | (RbCl-17% Ag/Al <sub>2</sub> O <sub>3</sub> )                                   | 225 | 0:1:1 | 18.7         | 0.1      | 96  |   |   |                                 |
|  |                     |   | 250 | 0:1:1 | 18.7         | 0.3      | 67  |   |   |                                 |
|  | U                   | (Ba(NO <sub>3</sub> ) <sub>2</sub> -<br>17% Ag/Al <sub>2</sub> O <sub>3</sub> ) | 225 | 0:1:1 | 18.3         | 0.8      | 90  |   |   |                                 |
|  |                     |   | 250 | 0:1:1 | 18.3         | 1.7      | 76  |   |   |                                 |
|  | V                   | (BaCl <sub>2</sub> -<br>17% Ag/Al <sub>2</sub> O <sub>3</sub> )                 | 250 | 0:1:1 | 18.4         | 0.3      | 83  |   |   |                                 |

Table 3 (Cont'd)

| Catalyst   | Temp.<br>°C | Reaction Parameters   |                                |   | C <sub>4</sub> H <sub>6</sub><br>Conversion,<br>% | Product<br>Selectivity,<br>%*** |
|--|-------------|---|--------------------------------|---|---|---------------------------------|
|  |             | Gas Feed<br>(He/O <sub>2</sub> /C <sub>4</sub> H <sub>6</sub> ) | Gas Flow<br>in mL<br>(STP)/min | Total<br>Gas Flow<br>in mL<br>(STP)/min |   |                                 |
| W (Br <sub>2</sub> -17% Ag/Al <sub>2</sub> O <sub>3</sub> )    | 250         | 0:1:1   | 18.2                           | 18.2                                    | 0.2   | 73                              |
| X (RbNO <sub>3</sub> -17% Ag/Al <sub>2</sub> O <sub>3</sub> )  | 225         | 0:1:1   | 18.4                           | 18.4                                    | 4.5   | 92                              |
| 250  | 0:1:1       | 18.4  | 18.4                           | 9.9                                     | 86  |                                 |
| D (19% Ag on Al <sub>2</sub> O <sub>3</sub> )                  | 250         | 0:1:1   | 17.4                           | 17.4                                    | 2.5   | 81                              |
| Y (CsCl-19% Ag/Al <sub>2</sub> O <sub>3</sub> )                | 250         | 0:1:1   | 17.5                           | 17.5                                    | 15.1  | 94                              |
| Z (CsBr-19% Ag/Al <sub>2</sub> O <sub>3</sub> )                | 250         | 0:1:1   | 18.2                           | 18.2                                    | 5.0   | 96                              |
| AA (CsNO <sub>3</sub> -19% Ag/Al <sub>2</sub> O <sub>3</sub> ) | 250         | 0:1:1   | 16.5                           | 16.5                                    | 15  | 77                              |

\*\*\*Product selectivity is reported as selectivity to epoxide based on the moles of olefin converted.

These results demonstrate that alkali metal and alkaline earth metal compounds increase the rate of butadiene monoxide formation and/or increase the selectivity to the desired product (relative to that obtained with unpromoted catalyst), with both rate and selectivity frequently being improved. The addition of halogens is also shown to be an effective means to increase the selectivity to butadiene monoxide.

The benefit of these additives is observed to be independent of the silver loading and the nature of the support employed.

EXAMPLE 4 - Effect of Various Catalyst Supports

A series of catalyst evaluations were carried out employing the same experimental setup described in Example 2. A variety of supported catalysts, prepared using different catalyst supports, were tested. The reaction parameters and results are set forth in Table 4.

Table 4

| Catalyst                                   | Reaction Parameters |  |                                | C <sub>4</sub> H <sub>6</sub> Conversion, % | Product Selectivity, %*** |
|--|---------------------|--|--------------------------------|---|---------------------------|
|  | Temp, °C            | Gas Feed (He/O <sub>2</sub> /C <sub>4</sub> H <sub>6</sub> ) | Total Gas Flow in mL (STP)/min |   |                           |
| A' (5% Ag/Al <sub>2</sub> O <sub>3</sub> ) | 250                 | 0:1:1  | 20                             | 1.5   | 74                        |
| CC (8.0% Ag/ZnO)                           | 250                 | 0:1:1  | 19.7                           | 0.2   | 70                        |
| DD (1.9% Ag/TiO <sub>2</sub> )             | 225                 | 0:1:1  | 20                             | 0.06  | 60                        |
| EE (5.2% Ag/TiO <sub>2</sub> )             | 225                 | 0:1:1  | 18.3                           | 0.03  | 53                        |
| FF (5% Ag/CaO)                             | 250                 | 0:1:1  | 19.0                           | 0.2   | 47                        |
| GG (5% Ag/SiO <sub>2</sub> )               | 250                 | 0:1:1  | 20                             | 1.1   | 87                        |
| HH (6.3% Ag/BaO)                           | 250                 | 0:1:1  | 20                             | 0.1   | 87                        |
| II (5% Ag/BN)                              | 200                 | 0:1:1  | 20                             | 0.2   | 68                        |
|  | 225                 | 0:1:1  | 20                             | 0.8   | 61                        |
| JJ (5% Ag/Si <sub>3</sub> N <sub>4</sub> ) | 225                 | 0:1:1  | 20                             | 0.1   | 66                        |
|  | 275                 | 0:1:1  | 20                             | 0.9   | 38                        |
| KK (5% Ag/SiC)                             | 225                 | 0:1:1  | 20                             | 0.1   | 70                        |
|  | 275                 | 0:1:1  | 20                             | 0.9   | 61                        |

\*\*\*Product selectivity is reported as selectivity to epoxide based on the moles of olefin converted.

These results demonstrate that a variety of supports are effective for the highly selective conversion of butadiene to butadiene monoxide. The results also indicate that alumina and silica are the presently preferred supports for use in the practice of the present invention.



## EXAMPLE 5 - Selective Epoxidation of a Variety of Olefins

The same experimental set-up described in Example 2 was employed with t-butylethylene as the olefin feed and 1.77 g of Catalyst P (see Table 1). Reaction parameters and results are set forth in Table 5.

Table 5  
t-Butylethylene (TBE) Oxidation

| Reaction Temp., °C | Gas Feed (He/TBE/O <sub>2</sub> ) | Total Gas Flow in mL (STP)/min | TBE Conversion, % | Product* Selectivity, %*** |
|--------------------|-----------------------------------|--------------------------------|-------------------|----------------------------|
| 250                | 25/1/25                           | 10                             | 0.6               | 41                         |
| 250                | 20/1/20                           | 10                             | 0.2               | >95                        |
| 250                | 85/1/85                           | 6                              | 1.0               | >95                        |
| 250                | 200/1/200                         | 6                              | 1.5               | >95                        |
| 275                | 60/1/60                           | 6                              | 1.9               | 43                         |
| 275                | 25/1/25                           | 6                              | 1.1               | 34                         |

\*Desired product is t-butylethylene monoxide.

\*\*\*Product selectivity is reported as selectivity to epoxide based on the moles of olefin converted.

These results demonstrate that olefins having no allylic hydrogens, e.g., t-butyl ethylene, can be selectively oxidized to the mono-epoxide derivative according to the practice of the present invention.

## EXAMPLE 6 - Effect of Organic Halide Co-Feed

The effect of the optional use of organic halide co-feeds such as 1,2-dichloroethane on the conversion of butadiene to butadiene monoxide over a promoted, supported silver catalyst was investigated.

For these reactions, a new catalyst was prepared by dissolving 132 g of silver nitrate (Kodak) in 300 mL of distilled water. To this solution was added 500 g of 1/4" diameter  $\text{Al}_2\text{O}_3$  rings (see Table I, footnote 3). The mixture was tumbled for 30 minutes at about 50°C, then the bulk water removed under reduced pressure at about 60°C. The resulting, preliminarily dried rings were then further dried, while being slowly tumbled for about two hours at 170°C in a forced air oven. The silver weight loading was determined by neutron activation analysis to be about 12 wt %. The resulting material was then calcined as described in Example 1.

After calcination, a portion of the silver-treated alumina was promoted by adding 200 g of the calcined catalyst to a solution of 224 mg CsCl and 32 mg  $\text{CsNO}_3$  in 120 mL of methanol. The rings were agitated in the methanol solution for about five minutes, then the bulk methanol was removed by rotary evaporation. The promoted catalyst was dried as described above at 170°C in a forced air oven, and then activated in a hydrogen-containing atmosphere as described in Example 1. The resulting catalyst is composed of 12 wt % Ag/ $\text{Al}_2\text{O}_3$  promoted with 1.12 mg CsCl/g catalyst and 0.16 mg  $\text{CsNO}_3$ /g catalyst (for a total promoter level of 0.99 mg Cs/g catalyst and 0.235 mg Cl/g catalyst. This catalyst is designated as Catalyst LL.

In similar fashion, Catalyst MM was prepared having a silver loading level of 12 wt % on alumina rings and promoted with 0.79 mg Cs/g catalyst and 0.21 mg Cl/g catalyst.

The oxidation of butadiene was then carried out using Catalysts LL or MM according to the procedure set out in Example 2. In addition, organic halide was added via a mass flow controller which delivered a gas stream containing 100 parts per million (by volume) of organic halide (helium diluent) to the reactant feed stream. By proper selection of flow rate for the 100 ppm organic halide-containing feed as diluted into the helium/olefin/oxygen feed stream, it was possible to very accurately and reproducibly control the level of organic halide in the process feed stream.

Table 6 illustrates the controlled and reversible effects of co-feeding an organic halide such as 1,2-dichloroethane to a reaction zone employed for the selective oxidation of butadiene to butadiene monoxide. The data are presented in the order in which the experiments were conducted. Reaction product analyses were conducted after about 60 minutes exposure to each concentration of dichloroethane.

Table 6

| Catalyst Activity (Catalyst MM) at 250 °C for Oxidation of Butadiene to Butadiene Monoxide* |                        |                                   |
|---|------------------------|-----------------------------------|
| Feed Concentration of 1,2-Dichloroethane, ppm   | % Butadiene Conversion | % Selectivity, Butadiene Monoxide |
| 0   | 20.4                   | 90.8                              |
| 20  | 16.2                   | 91.0                              |
| 5   | 19.3                   | 91.0                              |
| 10  | 17.5                   | 92.0                              |
| 0   | 21.0                   | 91.0                              |

\*Feed gas ratios:  $\text{He/butadiene/O}_2 = 4/1/1$ ; gas hourly space velocity was about  $600 \text{ hr}^{-1}$ .

The results in Table 6 demonstrate that the effect of organic halide on catalyst performance is reversible.

Another series of reactions were carried out with dichloroethane co-feed to determine the effect on product selectivity of long-term exposure of catalyst to organic halide co-feed.

Table 7

| Product Selectivity for Butadiene Oxidation at 250 °C with Catalyst LL with Dichloroethane Co-Feed* |                        |                                   |
|---|------------------------|-----------------------------------|
| Elapsed Time**  | % Butadiene Conversion | % Selectivity, Butadiene Monoxide |
| 0   | 22.8                   | 93.3                              |
| 18  | 20.6                   | 93.4                              |
| 40  | 18.6                   | 94.3                              |
| 90  | 16.3                   | 94.8                              |
| 113   | 15.2                   | 94.8                              |
| 161   | 13.6                   | 95.1                              |

\*Feed gas ratios: He/butadiene/O<sub>2</sub> = 4/1/1; gas hourly space velocity was about 600 hr<sup>-1</sup>.

\*\*Measured in minutes after introduction of 20 ppm dichloroethane was commenced.

The results in Table 7 demonstrate that organic halide co-feed causes an increase in selectivity to the desired epoxide product.

In order to demonstrate the stabilizing effect of organic halide co-feed on catalyst performance, two series of runs were carried out using Catalyst LL at a target reaction temperature of 228 °C - one reaction modified by the addition of 1,2-dichloroethane co-feed and the other carried out in the absence of co-feed. A fresh sample of Catalyst LL was used for each series of runs. Results are set forth in Table 8.

Table 8

Effect of Organic Halide Co-feed  
on Catalyst Stability\*

## A. No Organic Halide Co-feed

| Time on<br>Stream,<br>min (Rxn.<br>Temp, °C)** | % Conversion |        | % Selectivity,<br>Butadiene<br>Monoxide |
|--|--------------|--------|---|
|  | Butadiene    | Oxygen |   |
| 51   | 6.4          | 5.1    | 96.9                                    |
| 76   | 9.0          | 5.7    | 97.8                                    |
| 101  | 11.0         | 7.1    | 97.5                                    |
| 126  | 11.6         | 7.5    | 97.6                                    |
| 154  | 12.7         | 8.4    | 97.3                                    |
| 187  | 13.3         | 8.9    | 97.1                                    |
| 211  | 13.4         | 8.9    | 97.2                                    |
| 240  | 13.7         | 9.3    | 96.8                                    |
| 262 (230)                                      | 14.1         | 9.4    | 97.1                                    |
| 284 (231)                                      | 14.4         | 9.6    | 97.1                                    |
| 307 (233)                                      | 15.3         | 10.4   | 96.9                                    |
| 328 (236)                                      | 16.5         | 11.6   | 96.4                                    |
| 349 (239)                                      | 17.1         | 12.2   | 96.2                                    |
| 375 (243)                                      | 18.5         | 14.5   | 94.7                                    |
| 401 (256)                                      | 21.5         | 22.7   | 89.3                                    |
| 420 (313)                                      | 16.8         | 60.8   | 39.8                                    |
| 441 (402)                                      | 12.1         | 92.0   | 6.7                                     |
| 460 (422)                                      | 11.2         | 92.1   | 1.4                                     |

B. Co-feed of 4 ppm 1,2-dichloroethane (introduced  
after 270 minutes on stream)

| Time on<br>Stream,<br>min. | % Conversion |        | % Selectivity,<br>Butadiene<br>Monoxide |
|----------------------------|--------------|--------|---|
|                            | Butadiene    | Oxygen |   |
| 73                         | 7.4          | 4.6    | 97.9                                    |
| 103                        | 9.4          | 5.9    | 97.8                                    |
| 128                        | 11.5         | 6.3    | 97.6                                    |
| 157                        | 12.9         | 7.7    | 97.3                                    |
| 180                        | 13.6         | 8.8    | 97.3                                    |
| 243                        | 14.7         | 10.4   | 96.4                                    |
| 266***                     | 14.9         | 10.4   | 96.4                                    |
| 292                        | 14.3         | 10.0   | 96.5                                    |
| 324                        | 14.9         | 10.5   | 96.3                                    |
| 351                        | 14.9         | 10.5   | 96.3                                    |
| 377                        | 14.8         | 10.4   | 96.4                                    |

Table 8 (Cont'd.)

| Time on<br>Stream,<br>min. | % Conversion |        | % Selectivity,<br>Butadiene<br>Monoxide |
|----------------------------|--------------|--------|---|
|                            | Butadiene    | Oxygen |   |
| 404                        | 15.0         | 10.8   | 96.2                                    |
| 436                        | 14.6         | 10.3   | 96.3                                    |
| 464                        | 15.0         | 10.7   | 96.2                                    |
| 491                        | 15.2         | 10.7   | 96.3                                    |
| 514                        | 14.8         | 10.0   | 96.9                                    |
| 537                        | 15.2         | 10.5   | 96.7                                    |

\*Feed gas ratios He/butadiene/O<sub>2</sub> = 4/1/1; gas hourly space velocity was about 2200 hr<sup>-1</sup>

\*\*Reaction temperature was 228°C unless noted otherwise; temperature excursions are due to exothermic reaction resulting from uncontrolled rates of reaction.

\*\*\*Organic halide co-feed commenced at 270 minutes on stream.

The results in Table 8A illustrate the problem of catalyst instability over an extended reaction period. After several hours on stream, the temperature of the catalyst bed begins to increase dramatically. As the temperature of the catalyst bed increased, it was not possible to maintain the catalyst bed at the desired temperature, due to uncontrolled rate of reaction. In addition, selectivity to the desired epoxide product falls off dramatically.

In contrast, the results in Table 8B demonstrate the stabilizing effect exerted by organic halide co-feed. Catalyst performance is maintained essentially constant over many hours of reaction, still performing at good conversion levels and at very high selectivities about nine hours after reaction was commenced. Note also that at the low level of organic halide employed (4 ppm), the steady state levels of conversion/selectivity obtained without added organic halide (See Table 8A; butadiene conversion about 13%, selectivity to epoxide about 97%) are maintained essentially unchanged (see Table 8B) in the presence of organic halide. Thus, it is apparent that a concentration of organic halide co-feed can be selected so as to maintain virtually any desired steady state level of catalytic activity.

Another series of reactions were carried out to demonstrate the effect of a variety of organic halide co-feeds on the activity of supported silver catalysts used for the oxidation of butadiene to butadiene monoxide. For all the runs summarized in Table 9, reaction temperature was 225°C, feed composition was He/butadiene/O<sub>2</sub> = 4/1/1, gas hourly space velocity was about 2200 hr<sup>-1</sup>, and the catalyst employed was Catalyst LL.

Table 9

Effects of Various Organic Halides on Catalytic Activity and Selectivity to Butadiene Monoxide

| Run No. | Organic Halide,* ppm | Elapsed time, min. | % Butadiene Conversion | % Selectivity, Butadiene Monoxide |
|---------|----------------------|--------------------|------------------------|-----------------------------------|
| 1       | —                    | 0                  | 12.3                   | 97.9                              |
|         | DCP, 5               | 22                 | 10.3                   | 98.2                              |
|         | DCP, 5               | 44                 | 10.1                   | 98.4                              |
|         | —                    | 67                 | 12.4                   | 97.8                              |
|         | —                    | 85                 | 13.3                   | 97.5                              |
| 2       | —                    | 0                  | 13.3                   | 97.5                              |
|         | DCM, 30              | 23                 | 12.6                   | 97.6                              |
|         | DCM, 30              | 46                 | 12.4                   | 97.7                              |
|         | —                    | 63                 | 13.9                   | 97.7                              |
|         | —                    | 80                 | 14.5                   | 97.5                              |
| 3       | —                    | 0                  | 14.5                   | 97.5                              |
|         | MC, 30               | 17                 | 14.3                   | 97.4                              |
|         | MC, 30               | 39                 | 14.2                   | 97.3                              |
|         | —                    | 56                 | 14.7                   | 97.2                              |
| 4       | —                    | 0                  | 15.4                   | 96.3                              |
|         | TCE, 2.5             | 18                 | 11.8                   | 97.8                              |
|         | TCE, 2.5             | 37                 | 11.0                   | 97.9                              |
|         | —                    | 61                 | 13.4                   | 97.3                              |
|         | —                    | 84                 | 14.6                   | 97.5                              |
| 5       | —                    | 0                  | 14.6                   | 97.5                              |
|         | DCE, 2.5             | 14                 | 13.9                   | 97.5                              |
|         | DCE, 2.5             | 37                 | 14.0                   | 97.4                              |
|         | —                    | 57                 | 15.1                   | 97.3                              |
|         | —                    | 75                 | 15.3                   | 97.1                              |
| 6       | —                    | 0                  | 15.3                   | 97.1                              |
|         | VC, 30               | 33                 | 14.7                   | 97.0                              |
|         | —                    | 38                 | 15.7                   | 96.9                              |
| 7       | —                    | 0                  | 14.0                   | 96.3                              |
|         | VB, 5                | 34                 | 12.0                   | 96.9                              |
|         | —                    | 57                 | 12.9                   | 96.5                              |
|         | —                    | 112                | 13.7                   | 96.3                              |
| 8       | —                    | 0                  | 13.7                   | 96.3                              |
|         | EB, 5                | 10                 | 7.3                    | 97.8                              |
|         | —                    | 38                 | 12.7                   | 96.5                              |
|         | —                    | 95                 | 13.4                   | 96.2                              |

Table 9 (Cont'd)

| Run<br>No. | Organic<br>Halide,*<br>ppm | Elapsed<br>time,<br>min. | %<br>Butadiene<br>Conversion | %<br>Selectivity,<br>Butadiene<br>Monoxide |
|------------|----------------------------|--------------------------|------------------------------|--|
| 9          | —                          | 0                        | 13.4                         | 96.2                                       |
|            | DBE, 5                     | 37                       | 9.8                          | 96.6                                       |
|            | DBE, 5                     | 60                       | 9.4                          | 97.3                                       |
|            | —                          | 82                       | 10.8                         | 96.5                                       |
|            | —                          | 163                      | 11.3                         | 96.1                                       |

\*DCP = 1,2-dichloropropane  
 DCM = dichloromethane  
 MC = methyl chloride  
 TCE = trichloroethylene  
 DCE = 1,2-dichloroethylene  
 VC = vinyl chloride  
 VB = vinyl bromide  
 EB = ethyl bromide  
 DBE = 1,2-dibromoethane

For each organic halide investigated, the catalyst activity (butadiene conversion) and selectivity (molar % selectivity to butadiene monoxide) were established both before organic halide addition, and after organic halide co-feed has been stopped. Thus, the values presented above in Table 9 as "0" time points (designated by a "-") represent steady-state values for a given run immediately prior to introduction of organic halide co-feed. Conversion/selectivity values are recorded for one or two data points after organic halide co-feed was introduced. Then one or two data points are recorded after organic halide co-feed was stopped (also designated by a "-").

The return of conversion/selectivity values to their pre-co-feed values shortly after co-feed is removed is indicative of the reversible and controlled nature of the moderating effect of each of the tested co-feeds on catalyst performance. A decline in butadiene conversion and an increase in selectivity to butadiene monoxide during organic halide addition is indicative of the moderating effect of the organic halide co-feed.

#### EXAMPLE 7 - Comparative Oxidation Reactions

We attempted to repeat the oxidation of olefins higher than ethylene (such as propylene, 1-butene, 2-butene, etc.) as suggested by Brengle & Stewart in U.S. 2,709,173. In efforts to follow the teachings of the reference, catalyst composition (5% Ag/Al<sub>2</sub>O<sub>3</sub>) and reaction parameters as set forth in the reference were followed as closely as possible.

The reaction parameters employed and results obtained are set forth in Table 10.

Table 10

| Catalyst | Reaction Parameters |                                      |                                 | Feed Conversion, % | Product Selectivity, % |         |
|----------|---------------------|--------------------------------------|---------------------------------|--------------------|------------------------|---------|
|          | Temp. °C            | Gas Feed (He/O <sub>2</sub> /olefin) | Total Gas Flow in mL (STP)/min. |                    | CO <sub>2</sub>        | Epoxide |
| A'       | 250                 | 3:1:1                                | 25                              | 12                 | 53                     | 47      |
| A'       | 250                 | 3:1:1                                | 24                              | 7                  | 92                     | 0       |
| A'       | 250                 | 3:1:1                                | 23                              | 3                  | 92                     | 0       |
| A'       | 250                 | 3:1:1                                | 52.2                            | 2                  | 98                     | 0       |

These results confirm the suggestions of the literature, e.g., "Oxidation of butadiene with Ag<sub>2</sub>O at 551°K (278°C) by means of pulse technique gave only CO<sub>2</sub> and a small amount of acrylaldehyde." [Bull. Chem. Soc., Jap. 51, 3061-3062 (1978)], and "Silver and silver oxide catalysts, although suitable for the



oxidation of ethylene to ethylene oxide, do not seem to be similarly effective for the oxidation of the four-carbon olefins." [Ind. and Eng. Chem., 44, 594-603 (1952)]. The data set forth in Table 10 demonstrate that propylene, 1-butene and 2-butene are converted almost exclusively to CO<sub>2</sub>, with no observable epoxide formation.

5 These data refute the suggestion by Brengle and Stewart that the "lower molecular weight hydrocarbon olefins in particular are adaptable to this invention [preparation of olefin oxides]. Those which are normally gaseous, such as ethylene, propene, butene-1, butene-2 and butadiene, for example, are more suitable, with ethylene being preferred." [See Col. 2, 1. 64-68]. The data set forth above confirm the suggestions of the art, i.e., that silver catalyzed oxidation is effective only for the production of epoxide from ethylene.

10 The more recent disclosures of Rao in U.S. 4,429,055 and U.S. 4,474,977 are consistent with the suggestions of the above-cited prior art. Rao determined that among the lower olefins, only ethylene can be selectively directly epoxidized. When Rao carried out the oxidation of propylene, 1-butene and 1, 3-butadiene under epoxidation conditions, no epoxide product was observed. For example, propylene conversion was calculated to be 46.1% based on the content of oxygen in the feed, with the primary product formed being acrolein (28.8% selectivity). The only other products of propylene oxidation were CO<sub>2</sub> and H<sub>2</sub>O.

Similarly, when Rao evaluated the oxidation of 1, 3-butadiene, the observed products were furan, acrolein, dihydrofuran and trihydrofuran:

20 The selectivity to furan is 22.4% and to acrolein is 5.1%. Gas chromatographic analysis shows two other peaks besides furan and acrolein. They have retention times the same as a mixture of dihydrofuran and trihydrofuran.

See Col. 4 lines 1-5 of '997. Thus, Rao, consistently with all other relevant prior art, neither discloses nor suggests the selective formation of mono-epoxides from olefins such as butadiene, i.e., olefins having no allylic hydrogens.

25 The examples have been provided merely to illustrate the practice of our invention and should not be read so as to limit the scope of our invention or the appended claims in any way. Reasonable variations and modifications, not departing from the essence and spirit of our invention, are contemplated to be within the scope of patent protection desired and sought.

### 30 Claims

1. A process for the selective epoxidation of N-vinylpyrrolidone or olefins having the structure:

35



40

wherein each R is independently selected from:

- a) hydrogen,
- b) aryl and substituted aryl groups having in the range of 7 up to 20 carbon atoms,
- c) tertiary alkyl groups of the formula:


45




50

where each R' is independently:  
R'',

55



or



where R'' is H, C<sub>1</sub>-C<sub>10</sub> alkyl or substituted alkyl, an aryl or substituted aryl group having 6 up to 20 carbon atoms, and n is a whole number from 0-12;

d)  $\text{CR}_3''-(\text{CR}_2'')_x\text{O}-$ , where x is a whole number from 1-12;

e)



f)  $\text{R}_2''\text{N}-$ ;

g)  $\text{R}''\text{S}-$ ;

h)  $\text{CR}_2'' = \text{CR}''\{\text{CR}'' = \text{CR}''\}_y$ , where y is an integer from 0-20; or

i)



where X is O, S or NR''; and m is an integer from 0 - 3.

with the proviso that said olefin have no allylic hydrogens and that at least one R-group not be hydrogen;

said process comprising contacting said olefin with a sufficient quantity of an oxygen-containing gas so as to maintain the molar ratio of olefin to oxygen in the range of 0.01 up to 20, in the presence of a silver-containing catalyst and from 0 up to 1000 ppm (by volume of total feed) of an organic halide having the structure  $\text{R}'''\text{X}$ , wherein R''' is a hydrocarbyl or halogenated hydrocarbyl radical having in the range of 1 up to 8 carbon atoms, and X is any one of the halogens, at a pressure in the range of 0.1 up to 100 atmospheres, at a temperature in the range of 75 up to 325 °C for a time sufficient to obtain olefin conversions in the range of 0.1 up to 75%.

2. A process in accordance with Claim 1 wherein said silver catalyst is a supported silver catalyst comprising in the range of 0-1 up to 75 weight % elemental silver.

3. A process in accordance with Claim 2 wherein said supported silver catalyst is supported on an inorganic support having a surface area no greater than about 50 m<sup>2</sup>/g.

4. A process in accordance with Claim 3 wherein said inorganic support is selected from:

silica,  
alumina,  
silica-alumina,  
titanium oxide,  
lanthanum oxide,  
magnesium oxide,  
boron nitride,  
boron carbide,  
silicon nitride,  
silicon carbide,  
zinc oxide,  
tin oxide,  
iron oxide,  
calcium oxide,  
barium oxide,

- strontium oxide,  
zirconium oxide,  
carbon,  
boron phosphate,  
5 zirconium phosphate,  
or mixtures of any two or more thereof.
- 10 5. A process in accordance with Claim 2 wherein said silver catalyst further comprises in the range of 0.001 up to 10 weight %, based on the total weight of catalyst, including support, of at least one promoter selected from:
- 15 the salts of alkali metals,  
the oxides of alkali metals,  
the salts of alkaline earth metals,  
the oxides of alkaline earth metals,  
organic halides,  
inorganic halides,  
acid halides, or  
elemental halogens,  
as well as mixtures of any two or more thereof.
- 20 6. A process in accordance with Claim 5 wherein said promoter is a halide salt of an alkali metal or a mixture of a halide salt and a nitrate salt of an alkali metal.
- 25 7. A process in accordance with Claim 1 wherein said olefin is selected from:
- butadiene,  
tertiarybutyl ethylene,  
vinyl furan,  
methyl vinyl ketone, or  
N-vinyl pyrrolidone,  
30 as well as mixtures of any two or more thereof.
8. A process in accordance with Claim 7 wherein said silver catalyst comprises:
- 35 in the range of about 1 up to 30 weight % silver,  
in the range of about 0.001 up to 10 weight percent of an alkali metal halide and, optionally, alkali metal nitrate, and  
an alumina support having a surface area of less than about 10 m<sup>2</sup>/g;  
wherein said weight percentages are based on the total weight of catalyst.
- 40 9. A process in accordance with Claim 7 wherein said silver catalyst comprises:
- in the range of about 2 up to 20 weight percent silver,  
in the range of 0.01 up to 2 weight percent of an alkali metal halide and, optionally, alkali metal nitrate,  
an alumina support having a surface area of less than about 1 m<sup>2</sup>/g;  
wherein said weight percentages are based on the total weight of catalyst.
- 45 10. A process in accordance with Claim 9 wherein said alkali metal salts are selected from cesium chloride, cesium bromide, or cesium nitrate.
- 50 11. A process in accordance with Claim 8 wherein said contacting is carried out at a temperature in the range of about 175 up to 250 °C, at a pressure in the range of about 1 up to 30 atmospheres for a time sufficient to obtain olefin conversions in the range of about 1 up to 50%.
12. A process in accordance with Claim 9 wherein said contracting is carried out at a temperature in the range of about 175 up to 250 °C, at a pressure in the range of about 1 up to 30 atmospheres for a time sufficient to obtain olefin conversions in the range of about 1 up to 50%.
- 55 13. A process in accordance with Claim 1 wherein said contracting is carried out in the presence of at least 0.1 ppm of said organic halide.

14. A process in accordance with Claim 13 wherein X is chlorine or bromine.
15. A process in accordance with Claim 14 wherein said organic halide is selected from:  
methyl chloride, methyl bromide, methylene chloride, methylene bromide, chloroform, bromoform, ethyl  
chloride, ethyl bromide, dichloroethane, dibromoethane, vinyl chloride, dichloroethylene, trich-  
loroethylene, dichloropropane, dibromopropane, dichloropropene, dibromopropene, chlorobutane,  
bromobutane, dichlorobutane, dibromobutane, chlorobutene, bromobutene, dichlorobutene,  
dibromobutene, mono-, di-, tri-, tetra- and pentachloropentanes or pentenes, mono-, di-, tri-, tetra- and  
pentabromopentanes or pentenes, cyclopentylchloride, cyclopentylbromide, mono-, di-, tri-, tetra-,  
penta- and hexachlorohexanes or hexenes, mono-, di-, tri-, tetra-, penta- and hexabromohexanes or  
hexenes, cyclohexylchloride, cyclohexylbromide, chlorobenzene, bromobenzene, chlorotoluene,  
bromotoluene, benzyl chloride, benzyl bromide, mono-, di-, tri-, tetra-, penta-, hexa- and heptach-  
loroheptanes or heptenes, mono-, di-, tri-, tetra-, penta-, hexa- and heptabromoheptanes or heptenes,  
chlorocycloheptane, bromocycloheptane, mono-, di-, tri-, tetra-, penta-, hexa-, hepta- and octachlorooct-  
anes or octenes, mono-, di-, tri-, tetra-, penta-, hexa-, hepta-, and octabromooctanes or octenes; as  
well as mixtures of any two or more thereof.
16. A process in accordance with Claim 13 wherein said organic halide is co-fed to the reaction zone in  
admixture with the olefin to be oxidized and/or the oxygen-containing gas.
17. A process in accordance with Claim 13 wherein said organic halide is fed to the reaction zone  
independently of the introduction of the olefin to be oxidized.
18. A process in accordance with Claim 1 wherein said oxygen-containing gas is selected from:  
air,  
inert gas diluted air,  
inert gas diluted oxygen,  
oxygen-enriched air, or  
substantially purified oxygen.

# Patentansprüche

1. Verfahren für die selektive Epoxidation von N-Vinylpyrrolidon oder Olefinen der Struktur:




worin R jeweils unabhängig voneinander ausgewählt ist aus:


- a) Wasserstoff,
- b) Aryl- und substituierten Arylgruppen mit 7 bis zu 20 Kohlenstoffatomen;
- c) tertiären Alkylgruppen der Formel:



worin R' jeweils unabhängig voneinander ausgewählt ist aus:  
R'',



oder



worin R<sup>II</sup> steht für H, C<sub>1</sub>-C<sub>10</sub>-Alkyl oder substituiertes Alkyl, eine Aryl- oder substituierte Arylgruppe mit 6 bis zu 20 Kohlenstoffatomen und n eine ganze Zahl von 0 - 12;

d) CR<sub>3</sub><sup>II</sup>-(CR<sub>2</sub><sup>II</sup>)<sub>x</sub>-O-, worin x eine ganze von 1 - 12 ist;

e)



f) R<sub>2</sub><sup>II</sup> N-;

g) R<sup>II</sup> S-;

h) CR<sub>2</sub><sup>II</sup> = CR<sup>II</sup>{CR<sup>II</sup> = CR<sup>II</sup>}<sub>y</sub>, worin y eine ganze Zahl von 0 - 20 ist; oder

i)



worin X für O, S oder NR<sup>II</sup> steht; und worin m eine ganze Zahl von 0 - 3 ist, wobei gilt, daß das Olefin keine allylischen Wasserstoffatome aufweist, und daß mindestens eine R-Gruppe kein Wasserstoffatom ist;

wobei das Verfahren umfaßt die Kontaktierung des Olefins mit einer ausreichenden Menge eines Sauerstoff enthaltenden Gases, derart, daß das molare Verhältnis von Olefin zu Sauerstoff im Bereich von 0,01 bis zu 20 gehalten wird, in Gegenwart eines Silber enthaltenden Katalysators und 0 bis zu 1000 ppm (bezogen auf das Volumen der gesamten Einspeisung) eines organischen Halogenides der Struktur R<sup>II</sup>X, worin R<sup>II</sup> ein Kohlenwasserstoffrest oder ein halogener Kohlenwasserstoffrest mit 1 bis zu 8 Kohlenstoffatomen ist und X ein beliebiges Halogenatom, bei einem Druck im Bereich von 0,1 bis zu 100 Atmosphären, bei einer Temperatur im Bereich von 75 bis zu 325 °C, eine solche Zeitspanne lang, die ausreicht, um Olefin-Umwandlungen im Bereich von 0,1 bis zu 75 % zu erzielen.

2. Verfahren nach Anspruch 1, bei dem der Silberkatalysator ein einen Träger aufweisender Silberkatalysator ist mit 0,1 bis zu 75 Gew.-% elementarem Silber.
3. Verfahren nach Anspruch 2, bei dem der einen Träger aufweisende Silberkatalysator einen anorganischen Träger mit einer Oberfläche von nicht größer als etwa 50 m<sup>2</sup>/g aufweist.
4. Verfahren nach Anspruch 3, bei dem der anorganische Träger ausgewählt ist aus:
  - Kieselsäure,
  - Aluminiumoxyd,
  - Kieselsäure-Aluminiumoxyd,
  - Titanoxyd,
  - Lanthanoxyd,
  - Magnesiumoxyd,
  - Bornitrid,
  - Borcarbid,
  - Siliziumnitrid,
  - Siliziumcarbid,
  - Zinkoxyd,
  - Zinnoxid,

- Eisenoxyd,  
Kalziumoxyd,  
Bariumoxyd,  
Strontiumoxyd,  
5 Zirkoniumoxyd,  
Kohlenstoff,  
Borophosphat,  
Zirkoniumphosphat  
oder Mischungen von zwei oder mehreren hiervon.
- 10 5. Verfahren nach Anspruch 2, bei dem der Silberkatalysator weiterhin aufweist, bezogen auf das Gesamtgewicht von Katalysator, einschließlich Träger 0,001 bis zu 10 Gew.-% mindestens eines Promoters, ausgewählt aus:  
den Salzen von Alkalimetallen,  
15 den Oxyden von Alkalimetallen,  
den Salzen von Erdalkalimetallen,  
den Oxyden von Erdalkalimetallen,  
organischen Halogeniden,  
anorganischen Halogeniden,  
20 Säurehalogeniden oder  
elementaren Halogenen,  
wie auch Mischungen von zwei dieser Verbindungen oder mehreren hiervon.
6. Verfahren nach Anspruch 5, bei dem der Promoter ein Halogenidsalz eines Alkalimetalles oder eine  
25 Mischung aus einem Halogenidsalz und einem Nitratsalz eines Alkalimetalles ist.
7. Verfahren nach Anspruch 1, bei dem das Olefin ausgewählt ist aus:  
Butadien,  
tert.-Butylethylen,  
30 Vinylfuran,  
Methylvinylketon oder  
N-Vinylpyrrolidon,  
oder Mischungen von zwei oder mehreren Verbindungen hiervon.
- 35 8. Verfahren nach Anspruch 7, bei dem der Silberkatalysator umfaßt:  
etwa 1 bis zu 30 Gew.-% Silber,  
etwa 0,001 bis zu 10 Gew.-% eines Alkalimetallhalogenides und gegebenenfalls Alkalimetallnitrat und  
einen Aluminiumoxydträger mit einem Oberflächenbereich von weniger als etwa 10 m<sup>2</sup>/g;  
40 wobei die Gewichts-Prozentsätze sich auf das Gesamtgewicht des Katalysators beziehen.
9. Verfahren nach Anspruch 7, bei dem der Silberkatalysator umfaßt:  
etwa 2 bis zu 20 Gew.-% Silber,  
0,01 bis zu 2 Gew.-% eines Alkalimetallhalogenides und gegebenenfalls Alkalimetallnitrat ,  
einen Aluminiumoxydträger mit einem Oberflächenbereich von weniger als etwa 1 m<sup>2</sup>/g;  
45 wobei die Gewichts-Prozentsätze sich auf das Gesamtgewicht des Katalysators beziehen.
10. Verfahren nach Anspruch 9, bei dem die Alkalimetallsalze aus Cäsiumchlorid, Cäsiumbromid und Cäsiumnitrat ausgewählt sind.
- 50 11. Verfahren nach Anspruch 8, bei dem das Kontaktieren bei einer Temperatur im Bereich von etwa 175 bis zu 250 °C, bei einem Druck im Bereich von etwa 1 bis zu 30 Atmosphären und eine solche Zeitspanne lang erfolgt, die ausreicht, um Olefin-Umwandlungen im Bereich von etwa 1 bis zu 50 % zu erzielen.
- 55 12. Verfahren nach Anspruch 9, bei dem das Kontaktieren bei einer Temperatur im Bereich von etwa 175 bis zu 250 °C bei einem Druck im Bereich von etwa 1 bis zu 30 Atmosphären eine solche Zeitspanne lang durchgeführt wird, die ausreicht, um Olefin-Umwandlungen im Bereich von etwa 1 bis zu 50 % zu erzielen.

13. Verfahren nach Anspruch 1, bei dem das Kontaktieren in Gegenwart von mindestens 0,1 ppm des organischen Halogenides durchgeführt wird.

14. Verfahren nach Anspruch 13, bei dem X für Chlor oder Brom steht.

15. Verfahren nach Anspruch 14, bei dem das organische Halogenid ausgewählt ist aus:

Methylchlorid, Methylbromid, Methylenchlorid, Methylenbromid, Chloroform, Bromoform, Ethylchlorid, Ethylbromid, Dichloroethan, Dibromoethan, Vinylchlorid, Dichloroethylen, Trichloroethylen, Dichloropropan, Dibromopropan, Dichloropropen, Dibromopropen, Chlorobutan, Bromobutan, Dichlorobutan, Dibromobutan, Chlorobuten, Bromobuten, Dichlorobuten, Dibromobuten, Mono-, Di-, Tri-, Tetra- und Pentachloropentanen, oder Pentenen, Mono-, Di-, Tri-, Tetra- und Pentabromopentanen oder Pentenen, Cyclopentylchlorid, Cyclopentylbromid, Mono-, Di-, Tri-, Tetra-, Penta- und Hexachlorohexanen oder Hexenen, Mono-, Di-, Tri-, Tetra-, Penta- und Hexabromohexanen oder Hexenen, Cyclohexylchlorid, Cyclohexylbromid, Chlorobenzol, Bromobenzol, Chlorotoluol, Bromotoluol, Benzylchlorid, Benzylbromid, Mono-, Di-, Tri-, Tetra-, Penta-, Hexa- und Heptachloroheptanen oder Heptenen, Mono-, Di-, Tri-, Tetra-, Penta-, Hexa- und Heptabromoheptanen oder Heptenen, Chlorocycloheptan, Bromocycloheptan, Mono-, Di-, Tri-, Tetra-, Penta-, Hexa-, Hepta- und Octachlorooctanen oder Octenen, Mono-, Di-, Tri-, Tetra-, Penta-, Hexa-, Hepta- und Octobromooctanen oder Octenen, wie auch Mischungen von zwei oder mehreren dieser Verbindungen.

16. Verfahren nach Anspruch 13, bei dem das organische Halogenid in die Reaktionsmischung zusammen mit dem zu oxidierenden Olefin und/oder dem Sauerstoff enthaltenden Gas eingespeist wird.

17. Verfahren nach Anspruch 13, bei dem das organische Halogenid in die Reaktionszone unabhängig von der Einführung des zu oxidierenden Olefins eingespeist wird.

18. Verfahren nach Anspruch 1, bei dem das Sauerstoff enthaltende Gas ausgewählt ist aus:

Luft,  
mit einem Inertgas verdünnter Luft,  
mit einem Inertgas verdünntem Sauerstoff,  
mit Sauerstoff angereicherter Luft, oder  
praktisch reinem Sauerstoff.


## Revendications

1. Procédé pour l'époxydation sélective de la N-vinylpyrrolidone ou d'oléfines de formule :




dans laquelle chaque R est choisi indépendamment parmi :


- l'hydrogène,
- les groupes aryles et aryles substitués en C<sub>7</sub>-C<sub>20</sub>
- les groupes alkyles tertiaires de formule :



dans laquelle chaque R' est indépendamment :  
R'',



ou



où R'' est H, un alkyle ou alkyle substitué en C<sub>1</sub>-C<sub>10</sub>, un aryle ou aryle substitué en C<sub>6</sub>-C<sub>20</sub> et n est un entier de 0 à 12 ;

d)  $\text{CR}_3''(\text{CR}_2'')_x-\text{O}-$ , où x est un entier de 1 à 12 ;

e)

f)  $\text{R}_2''\text{N}-$  ;g)  $\text{R}''\text{S}-$  ;h)  $\text{CR}_2'' = \text{CR}''\{\text{CR}'' = \text{CR}''\}_y$ , où y est un entier de 0 à 20 ; ou

i)



où X est O, S ou NR'' ; et m est un entier de 0 à 3 avec la condition que ladite oléfine n'ait pas d'hydrogènes allyliques et qu'au moins un R ne soit pas l'hydrogène ;

ledit procédé comprenant la mise en contact de ladite oléfine avec une quantité suffisante d'un gaz contenant l'oxygène pour maintenir le rapport molaire de l'oléfine à l'oxygène dans l'intervalle de 0,01 à 20, en présence d'un catalyseur contenant de l'argent et de 0 à 1000 ppm (en volume de la charge totale) d'un halogénure organique de formule R''X dans laquelle R'' est un radical hydrocarbyle ou hydrocarbyle halogéné en C<sub>1</sub>-C<sub>8</sub> et X est l'un quelconque des halogènes, sous une pression dans l'intervalle de 0,1 à 100 atmosphères, à une température dans l'intervalle de 75 à 325 °C pendant une durée suffisante pour obtenir des conversions de l'oléfine dans l'intervalle de 0,1 à 75%.

2. Procédé selon la revendication 1, dans lequel ledit catalyseur à l'argent est un catalyseur à l'argent sur support comprenant de 0,1 à 75% en poids d'argent élémentaire.
3. Procédé selon la revendication 2, dans lequel ledit catalyseur à l'argent sur support est déposé sur un support inorganique ayant une surface spécifique de pas plus d'environ 50 m<sup>2</sup>/g.
4. Procédé selon la revendication 3, dans lequel ledit support inorganique est choisi parmi :  
la silice,  
l'alumine,  
la silico-alumine,  
l'oxyde de titane,  
l'oxyde de lanthane,



- l'oxyde de magnésium,  
 le nitrure de bore,  
 le carbure de bore,  
 le nitrure de silicium,  
 le carbure de silicium,  
 l'oxyde de zinc,  
 l'oxyde d'étain,  
 l'oxyde de fer,  
 l'oxyde de calcium,  
 l'oxyde de baryum,  
 l'oxyde de strontium,  
 l'oxyde de zirconium,  
 le carbone,  
 le phosphate de bore,  
 le phosphate de zirconium,  
 ou des mélanges de deux ou plusieurs quelconques d'entre eux.
5. Procédé selon la revendication 2, dans lequel ledit catalyseur à l'argent comprend en outre 0,001 à 10% en poids, par rapport au poids total du catalyseur, y compris le support, d'au moins un promoteur choisi parmi :
- les sels de métaux alcalins,  
 les oxydes de métaux alcalins,  
 les sels de métaux alcalino-terreux,  
 les oxydes de métaux alcalino-terreux,  
 les halogénures organiques,  
 les halogénures inorganiques,  
 les halogénures d'acides,  
 ou les halogènes élémentaires,  
 ainsi que les mélanges de deux ou plusieurs quelconques d'entre eux.
6. Procédé selon la revendication 5, dans lequel ledit promoteur est un halogénure d'un métal alcalin ou un mélange d'un halogénure et d'un nitrate d'un métal alcalin.
7. Procédé selon la revendication 1, dans lequel ladite oléfine est choisie parmi :
- le butadiène,  
 le tertioibutyléthylène,  
 le vinylfuranne,  
 la méthylvinylcétone ou  
 la N-vinylpyrrolidone,  
 ainsi que les mélanges de deux ou plusieurs quelconques d'entre elles.
8. Procédé selon la revendication 7, dans lequel ledit catalyseur à l'argent comprend :
- d'environ 1 à 30% en poids d'argent,  
 d'environ 0,001 à 10% en poids d'un halogénure de métal alcalin et éventuellement d'un nitrate de métal alcalin et  
 un support d'alumine ayant une surface spécifique de 10 m<sup>2</sup>/g ;  
 dans lequel lesdits pourcentages en poids sont rapportés au poids total du catalyseur.
9. Procédé selon la revendication 7, dans lequel ledit catalyseur à l'argent comprend :
- d'environ 2 à 20% en poids d'argent,  
 de 0,01 à 2% en poids d'un halogénure de métal alcalin et éventuellement de nitrate de métal alcalin,  
 d'un support d'alumine ayant une surface spécifique de moins d'environ 1 m<sup>2</sup>/g ;  
 dans lequel lesdits pourcentages en poids sont rapportés au poids total du catalyseur.
10. Procédé selon la revendication 9, dans lequel lesdits sels de métaux alcalins sont choisis parmi le chlorure de césium, le bromure de césium et le nitrate de césium.

11. Procédé selon la revendication 8, dans lequel ladite mise en contact est effectuée à une température dans l'intervalle d'environ 175 à 250 °C, sous une pression dans l'intervalle d'environ 1 à 30 atmosphères pendant une durée suffisante pour obtenir des conversions de l'oléfine dans l'intervalle d'environ 1 à 50%.
12. Procédé selon la revendication 9, dans lequel ladite mise en contact est effectuée à une température dans l'intervalle d'environ 175 à 250 °C sous une pression dans l'intervalle d'environ 1 à 30 atmosphères pendant une durée suffisante pour obtenir des conversions de l'oléfine dans l'intervalle d'environ 1 à 50%.
13. Procédé selon la revendication 1, dans lequel ladite mise en contact est effectuée en présence d'au moins 0,8 ppm dudit halogénure organique.
14. Procédé selon la revendication 13, dans lequel X est le chlore ou le brome.
15. Procédé selon la revendication 14, dans lequel ledit halogénure organique est choisi parmi les suivants :
- chlorure de méthyle, bromure de méthyle, chlorure de méthylène, bromure de méthylène, chloroforme, bromoforme, chlorure d'éthyle, bromure d'éthyle, dichloroéthane, dibromoéthane, chlorure de vinyle, dichloroéthylène, trichloroéthylène, dichloropropane, dibromopropane, dichloropropène, dibromopropène, chlorobutane, bromobutane, dichlorobutane, dibromobutane, chlorobutène, bromobutène, dichlorobutène, dibromobutène, mono-, di-, tri-, tétra- et pentachloropentanes ou pentènes, mono-, di-, tri-, tétra- et pentabromopentanes ou pentènes, chlorure de cyclopentyle, bromure de cyclopentyle, mono-, di-, tri-, tétra-, penta- et hexachlorohexanes ou hexènes, mono-, di-, tri-, tétra-, penta- et hexabromohexanes ou hexènes, chlorure de cyclohexyle, bromure de cyclohexyle, chlorobenzène, bromobenzène, chlorotoluène, bromotoluène, chlorure de benzyle, bromure de benzyle, mono-, di-, tri-, tétra-, penta-, hexa- et heptachloroheptanes ou heptènes, mono-, di-, tri-, tétra-, penta-, hexa- et heptabromoheptanes ou heptènes, chlorocycloheptane, bromocycloheptane, mono-, di-, tri-, tétra-, penta-, hexa-, hepta- et octachlorooctanes ou octènes, mono-, di-, tri-, tétra-, penta-, hexa-, hepta et octabromooctanes ou octènes ; ainsi que les mélanges de deux ou plusieurs quelconques d'entre eux.
16. Procédé selon la revendication 13, dans lequel ledit halogénure organique est introduit dans la zone de réaction en mélange avec l'oléfine à oxyder et/ou le gaz contenant de l'oxygène.
17. Procédé selon la revendication 13, dans lequel ledit halogénure organique est introduit dans la zone de réaction indépendamment de l'introduction de l'oléfine à oxyder.
18. Procédé selon la revendication 1, dans lequel ledit gaz contenant de l'oxygène est choisi parmi :
- l'air,  
l'air dilué par un gaz inerte,  
l'oxygène dilué par un gaz inerte,  
l'air enrichi en oxygène et  
l'oxygène essentiellement purifié.